

## Optical Low-pass Filter


### Terms and Definitions

**Optical Low-pass Filter:** This uses elements that separate ordinary and extraordinary beams of incident light to remove pseudo-signals.


**Separation Width:** The distance between the ordinary and extraordinary beams separated when light passes through an optical low-pass filter, and this is proportional to the width of the low-pass filter.

**Pseudo-signal:** Generated by solid-state image pickup devices, pseudo-signals causes horizontal lines to look jagged or the black-and-white lattice fringe to be colored.

**Spectral Characteristic:** This indicates transmittance with respect to light wavelength. A coating or glass is used for an optical low-pass filter in order to block out near-infrared light beams.




Example of how pseudo-signals are removed



(\* CZP: Acronym of Circular Zone Plate)

### Application

As shown in the figure below, this filter is used mainly as a spatial frequency low-pass filter for removing pseudo-signals from a camera.




## Optical Low-pass Filter

### Features


#### Single Plate-type Optical Low-pass Filter

1. A computer controlled grown synthetic quartz crystal ensures this filter has excellent characteristics as a birefringent plate.
2. IR-cut, AR coating, ITO Film and water-repellency coating are available upon request.



#### Bonding-type Optical Low-pass Filter

1. Pseudo-signals can be removed by combining a crystal phase plate (crystal wavelength plate), and an optical low-pass filter in the horizontal, vertical, or any direction of your choice.
2. Filter glass combination and coating are available upon request.




### Standard specifications

#### Single Plate-type Optical Low-pass Filter

Specifications	Standards
Separation width accuracy (thickness accuracy)	Specified separation width $\pm 0.5 \mu\text{m}$ (Specified thickness $\pm 0.05 \text{ mm}$ )
Outline size	Round plate of $\phi 5$ to 30 mm Square plate of 5 x 5 to 40.5 x 48 mm
Light axis accuracy	$44^\circ 50' \pm 60'$
Flatness	Max. 10 Newton rings ( $\lambda = 589 \text{ nm}$ )

Standard outline size (mm)

- (1/2-inch size)  
9×10 11×12
- (1/3-inch size)  
8.5×9
- (1/4-inch size)  
7.3×7.8
- (1/5-inch size)  
5.0×5.5




Low-pass filters of other outline sizes can be manufactured upon request.

#### Bonding-type Optical Low-pass Filter

Specifications	Standards
Outline size	Round plate of $\phi 5$ to 30 mm Square plate of 5 x 5 to 40.5 x 48 mm
Light axis accuracy	$44^\circ 50' \pm 60'$
Optical axis bonding accuracy	Specified angle $\pm 60'$
Flatness	Max. 20 Newton rings ( $\lambda = 589 \text{ nm}$ )

Standard outline size (mm)

- (1/2-inch size)  
9×10 11×12
- (1/3-inch size)  
8.5×9
- (1/4-inch size)  
7.3×7.8
- (1/5-inch size)  
5.0×5.5



(For single-lens reflex DSC)  
22×28 25.3×29.5 28×40

Bonding-type low-pass filters of other outline sizes can be manufactured upon request.

### Environment Resistance

The following reliability tests guarantee the specified optical characteristics of NDK's optical components.

Subjected to high temperature	For 96 hours at $+85^\circ \text{C}$
Subjected to low temperature	For 96 hours at $-40^\circ \text{C}$
Subjected to high temperature and high humidity	For 96 hours at $+60^\circ \text{C}$ and 95 %
Heat shock	10 cycles (one cycle is conducted for 30 minutes at $-40^\circ \text{C}$ and 30 minutes at $+85^\circ \text{C}$ )
Mechanical strength	No flaws after the surface is rubbed with absorbent cotton

## ■ Optical Low-pass Filter

### ● How to Determine Optical Low-pass Filter Specifications

When placing an order or asking for information, please inform us of the following items. (Check the boxes.)

1. Size of CCD used  
 1/2 inch                   :  1/3 inch                   :  1/4 inch                   :  1/5 inch


2. Number of pixels: \_\_\_\_\_

3. CCD model name: \_\_\_\_\_

4. Infrared absorption filter name: \_\_\_\_\_

5. Coating  
 Present                   :  Absent  
 (When coating is present)  
 •AR single layer    One surface                   :  Both surfaces  
 •AR multi-layer    One surface                   :  Both surfaces  
 •IR-Cut  
 •Others

6. Dimensions (part composition)  
 (a) × (b) × (c) : \_\_\_\_\_



	Part Name	Thickness	Tolerance	Angle between the Light Axis and the Principal Surface	In-surface Rotation Angle	Coating	
						A : AR single layer B : AR multi-layer C : IR-Cut coating D : None E : Others	
A						Both surfaces/One surface	A • B • C • D • E
B						Both surfaces/One surface	A • B • C • D • E
C						Both surfaces/One surface	A • B • C • D • E
D						Both surfaces/One surface	A • B • C • D • E
E						Both surfaces/One surface	A • B • C • D • E

\* Concerning optical low-pass filters other than square ones, please inform us of your individual specifications.

## ■ $\lambda/4$ and $\lambda/2$ Wavelength Plates

### ● Terms and Definitions

**Crystal Wavelength Plate:** An element that uses the velocity difference between ordinary and extraordinary light beams to create a phase difference between both beams; the difference is obtained by using the birefringence of a crystal. When this characteristic is used, a  $\lambda/4$  wavelength plate converts linearly-polarized light into circularly-polarized light, and a  $\lambda/2$  wavelength plate converts circularly-polarized light into linearly-polarized light with its polarization plane rotated by 90 degrees.

**Wavefront aberration:** This indicates the Peak-to-Valley difference of a measured wavefront as a unit of design wavelength: the Zygo Corporation's phase interference system is used to provide the data.

$$P - V = (\text{maximum phase angle} - \text{minimum phase angle})$$

**Extinction Ratio:** This indicates a value for the phase accuracy of a wavelength plate, and the conversion equation of the extinction ratio  $V$  [%] and phase difference  $\Gamma$  [deg] is as follows:

$$V [\%] = 100 \times \cos \Gamma$$

$$V = \frac{I_{o, 0} - I_{o, 90}}{I_{o, 0} + I_{o, 90}}$$

$$\Gamma = \frac{360}{\lambda} (n_e - n_o) \times t$$

$I_{o, 0}$  : Output in a parallel Nicol state

$I_{o, 90}$  : Output in an orthogonal Nicol state

$n_e$  : Refractive index of an extraordinary beam

$n_o$  : Refractive index of an ordinary beam

$t$  : Thickness of a phase plate

$\lambda$  : Design wavelength

### ● Application

As shown in the figure below, wavelength plates are used mainly for picking up optical information files (DVD, etc) to prevent the back-talk noise of laser beams.

